

PAINTED WOOD

BROWN
WHITE
GREY
CREAM



PAINTED WOOD

4 COLOURS

brown

white

grey

cream

2 SIZES

20x120 - 8"x48" Rett

10x120 - 4"x48" Rett



brown



white

1



grey



cream

PAINTED WOOD

brown

20x120 - 8"x48" Rett





PAINTED WOOD

brown


4

GRES PORCELLANATO SMALTATO


GLAZED PORCELAIN STONEWARE - GRES CERAME EMAILLE - GLASIERTES FEINSTEINZEUG - КЕРАМОГРАНИТ, ГЛАЗУРЬ НАНЕСЕНА ЦЫФРОВЫМ



1004700 10x120 - 4"x48" Rett




1004647 20x120 - 8"x48" Rett



BATTISCOPIA



1004708 9,8x120 - 37/8"x48"



V4


PAINTED WOOD

white


5



1004701 10x120 - 4"x48" Rett



1004648 20x120 - 8"x48" Rett



BATTISCOPIA



1004711 9,8x120 - 37/8"x48"



V4

PAINTED WOOD

grey


6

GRES PORCELLANATO SMALTATO


GLAZED PORCELAIN STONEWARE - GRES CERAME EMAILLE - GLASIERTES FEINSTEINZEUG - КЕРАМОГРАНИТ, ГЛАЗУРЬ НАНЕСЕНА ЦЫФРОВЫМ



1004702 10x120 - 4"x48" Rett




1004649 20x120 - 8"x48" Rett



BATTISCOPIA



1004710 9,8x120 - 3 7/8"x48"



V4


PAINTED WOOD

cream


7



1004703 10x120 - 4"x48" Rett



1004650 20x120 - 8"x48" Rett



BATTISCOPA



1004709 9,8x120 - 37/8"x48"



V4


PAINTED WOOD

mosaici


brown



1004716 MOSAICO INTRECCIO
30x30 - 11³/₄"x11³/₄"




1004712 MOSAICO ESAGONA
25x30 - 10"x11³/₄"




white




1004717 MOSAICO INTRECCIO
30x30 - 11³/₄"x11³/₄"





1004713 MOSAICO ESAGONA
25x30 - 10"x11³/₄"




grey




1004718 MOSAICO INTRECCIO
30x30 - 11³/₄"x11³/₄"




1004714 MOSAICO ESAGONA
25x30 - 10"x11³/₄"




cream



1004719 MOSAICO INTRECCIO
30x30 - 11³/₄"x11³/₄"



1004715 MOSAICO ESAGONA
25x30 - 10"x11³/₄"



8

IMBALLI - PACKING TABLE - TABLEAU DES EMBALLAGES - VERPACKUNGS TABELLE - УПАКОВКА

FORMATO SIZE	SCATOLA - BOX			PALLET		
	Pezzi - Pieces	m ²	KG	Scatole - Boxes	m ²	KG
20x120 - 8"x48" Rett	4	0,96	21,30	36	34,56	786,00
10x120 - 4"x48" Rett	8	0,96	20,00	36	34,56	740,00
30x30 - 11 ³ / ₄ "x11 ³ / ₄ " Mosaico Intreccio	5	0,45	9,00	60	27,00	560,00
25x30 - 10"x11 ³ / ₄ " Mosaico Esagona	5	0,38	8,00	60	22,50	500,00

GRES PORCELLANATO SMALTATO

GLAZED PORCELAIN STONEWARE

GRES CERAME EMAILLE

GLASIERTES FEINSTEINZEUG

КЕРАМОГРАНИТ, ГЛАЗУРЬ НАНЕСЕНА ЦЫФРОВЫМ



V4

Proprietà fisico chimiche/Physical-chemical properties Caracteristiques physiques-chimiques/physische Chemische eigenschaften	Norme/ Norms Noemes Normen	Valori presvalori prescritti / Required values Valeurs exigees / Vorgeschriebene werte		
Dimensioni Sizes Format Format	ISO 10545-2	Lunghezza e larghezza Length and width Longueur et largeur Länge und Breite	(± 0,75% 190 cm² < 410 ≤) (± 0,6 % > 410 cm2)	± 0,3% max ± 1,5 mm
		Rettilineità spigoli Linearity Rectitude de l'angularité Kantengeradheit	(± 0,5% max)	± 0,3% max ± 1,5 mm
		Ortogonalità Wedging Orthogonalité Rechtwinkligkeit	(± 0,6% max)	± 0,3% max ± 1,5 mm
		Planarità Warpage Planéité Ebenflächigkeit	(± 5% max)	± 0,5% max ± 1,5 mm
	ASTM C485		Warpage diagonal/edge ± 0,4%	
Spessore Thickness Épaisseur Stärke	ISO 10545-2		(± 5% max)	10 mm
Assorbimento d'acqua Water absorption Absorption d' eau Wasseraufnahme	ISO 10545-3		≤ 0,5% GRUPPO Bla GL	E ≤ 0,1% Bla GL
Resistenza a flessione e forza di rottura Moduls of rupture and breaking strength résistance à la flexion et force de rupture Biegefestigkeit und Bruchlast	ISO 10545-4		S ≥ 1300 N	S ≥ 1300 N
			R ≥ 35 N/mm²	R ≥ 35 N/mm² ²
Resistenza agli sbalzi termici Thermal shocks resistant Résistance aux variations thermiques Temperaturwechselbeständigkeit	ISO 10545-9		Requisito non previsto Not provided requirement Qualité pas previe Erfordernis nicht vorgesehen	Resistente Resistant Résistant Widerstandsfähigkeit
Resistenza al gelo Frost resistance Résistance au gel Froständigkeit	ISO 10545-12		Nessuna alterazione No alteration Aucune alteration Keine Änderung	Resistente Resistant Résistant Widerstandsfähigkeit
Resistenza alla abrasione della superficie di piastrelle smaltate Resistance to surface abrasion of glazed tiles Résistance à l'abrasion de la surface des carreaux émaillés Widerstand gegen Abrieb der Oberfläche der glasierten Fliesen	ISO 10545-7			Classe 4 Class 4 Classe 4 Gruppe 4
Coefficiente di dilatazione termica lineare (50°/400°) Linear thermal expansion coefficient (50°/400°) Dilatation thermique linéaire (50°/400°) Lineare Wärmeausdehnung (50°/400°)	ISO 10545-8			Metodo disponibile Test method available Méthode disponible Verfügbares Verfahren
Durezza della Superficie Surface resistance Dureté de la surface Ritzhärte der Oberfläche	EN 101			> 6
Resistenza all'attacco chimico (tranne acido fluoridrico) Resistance to chemical attack (except hydrofluoric acid) Résistance à l'attaque chimique (sauf acide fluoridrique) Säure-und Laugenbeständigkeit (außer Flußsäure)	ISO 10545-13		Come indicato dal produttore As indicated by manufacturer Comme indiqué par le producteur Wie vom Hersteller angegeben	Classe A - LA - HA Class A - LA - HA Classe A - LA - HA Gruppe A - LA - HA
Resistenza alle macchie Resistance to staining Résistance aux taches Fleckbeständigkeit	ISO 10545-14		CLASSE min. 3	Classe 5 Class 5 Classe 5 Gruppe 5
Coefficiente di attrito Coefficient of friction Coefficient de frottement Reibungskoeffizient	DIN 51130			R10
Resistenza alla scivolosità. Coefficiente di attrito medio Skid resistance. Average coefficient of friction Résistance au glissement. Coéfficient de frottement moyen Rutschfestigkeit. Mittlerer Reibungswert	DIN 51097			Classe B Class B Classe B Gruppe B
	B.C.R.A. (No Lapp)		μ > 0,40 (Wet) μ > 0,40 (Dry)	0,40 ≤ μ ≤ 0,74
	DCOF Acu Test (No Lapp)		≥ 0,42	μ ≥ 0,42
Variazione cromatica Colour shading Variations chromatiques Chromatische Abweichungen				V 4

CE

NGT SPA
VIA PLATONE 9
42048 RUBIERA (RE)
05
001NGT2013-07-01

EN 14411:2012

Piastrelle di ceramica pressate a secco,
con assorbimento di acqua E_s ≤ 0,5%,
per pavimentazioni interne ed esterne.

Dry pressed ceramic tile,
with water absorption E_s ≤ 0,5%,
for internal and external floorings.



